

Claims:

- Sub 1
A2
1. A web of material having at least two major sides, the web comprising:
a plurality of discrete regions on at least a first major side of the web; and
a plurality of stems extending from each discrete region;
wherein the plurality of stems are fused and formed to at least the first major side of
the web.
2. The web according to claim 1, wherein the plurality of stems are attached directly to
the first major side of the web.
3. The web according to claim 1, wherein the plurality of stems are comprised of a
thermoplastic material selected from the group consisting of: polyurethane, polyolefins,
polystyrenes, polycarbonates, polyester, polymethacrylate, ethylene vinyl acetate
copolymers, ethylene vinyl alcohol copolymers, polyvinylchloride, acrylate modified
ethylene vinyl acetate polymers, and ethylene acrylic acid copolymers.
4. The web according to claim 1, wherein the discrete regions cover between 5 and 25
percent of the first major side of the web.
5. The web according to claim 1, wherein at least a portion of the web is configured
and arranged to engage the plurality of stems.
- Sub 3
A3
- ~~6. The web according to claim 1, wherein the web comprises an elastic material.~~
7. The web according to claim 6, wherein the elastic material is selected from the
group consisting of: natural and synthetic rubbers; styrene block copolymers containing
isoprene, butadiene, or ethylene(butylene) blocks; metallocene-catalyzed polyolefins,
polyurethanes, and polydiorganosiloxanes.

8. ~~The web according to claim 1, wherein the web defines a localized plane, and the plurality of stems are oriented at a plurality of angles to the localized plane.~~

9. ~~The web according to claim 1, wherein one or more of the stems is shaped to provide directional hooking capability.~~

10. ~~The web according to claim 1, wherein the discrete regions are separated an average of approximately 0.05 and 30 centimeters from one another.~~

11. A method of making a web material having a plurality of stems extending from discrete regions of the web, the method comprising:

- (a) providing a web;
- (b) providing discrete quantities of a polymeric material at a temperature above its softening point;
- (c) fusing the discrete quantities of the polymeric material to the web; and
- (d) forming a plurality of stems in each of the discrete quantities of the polymeric material.

12. The method according to claim 11, wherein fusing the discrete quantities of polymeric material to the web occurs simultaneously with forming a plurality of stems in each of the discrete quantities of polymeric material.

13. The method according to claim 11, wherein the discrete quantities of polymeric material are provided by extruding molten polymer in a form selected from intermittent quantities and continuous ribbons.

14. The method according to claim 11, wherein the discrete quantities of polymeric material are provided by one or more rotating cutting blades positioned intermediate a source of polymeric material and the web, wherein the cutting blades cut the polymeric material into discrete quantities.



- [illegible]

ADD